



(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
17.05.2006 Bulletin 2006/20

(51) Int Cl.:
A61L 27/50 (2006.01)

(21) Application number: **03251687.4**

(22) Date of filing: **19.03.2003**

(54) **Intervertebral disk treatment using a crosslinking agent and an inactivating or stabilising agent**

Bandscheibenbehandlung mit einem Vernetzer und einem Inaktivator oder Stabilisator

Traitement de disque intervertébral avec un agent réticulant et un agent inactivant ou stabilisant

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IT LI LU MC NL PT RO SE SI SK TR**

(30) Priority: **19.03.2002 US 102075**

(43) Date of publication of application:
24.09.2003 Bulletin 2003/39

(73) Proprietor: **DePuy Spine, Inc.**
Raynham, MA 02767-0350 (US)

(72) Inventors:
• **Slivka, Michael Andrew**
Taunton, MA 02780 (US)

• **Serhan, Hassan**
South Easton, MA 02375 (US)

(74) Representative: **Belcher, Simon James**
Urquhart-Dykes & Lord LLP
Tower North Central
Merrion Way
Leeds LS2 8PA (GB)

(56) References cited:
WO-A-00/20021 **WO-A-00/62832**
WO-A-01/70151 **WO-A-01/76654**
WO-A-97/26847 **WO-A-03/020031**
US-A- 4 931 546

EP 1 346 736 B1

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

[0001] This invention relates to a kit for intervertebral disc treatment.

[0002] The intervertebral disc contains three major components: a nucleus pulposus (a fluid-like component comprising proteoglycans and collagen), an annulus fibrosis (a flexible, collagen-based ring surrounding the nucleus pulposus) and a pair of cartilaginous endplates which help enclose the nucleus pulposus within the annulus fibrosus. A normal, healthy nucleus pulposus acts much like a pressurized fluid by transferring and distributing compressive load to the annulus fibrosis, thereby causing a slight expansion of the annulus fibrosus. However, injury and/or degeneration of the intervertebral disc in the human spine can be caused by disc herniation, rupture of the annulus, prolapse of the nucleus pulposus, mechanical instability of the disc and/or dehydration of the disc, thereby leading to back pain. In addition, damage or degeneration of the annulus fibrosus in the form of a herniation, tear and/or crack reduces its ability to resist the tensile stresses conferred by the nucleus pulposus. Thus, the disc experiences excessive bulging that may result in spinal cord and/or nerve root impingement and subsequent back pain. Further, the nucleus pulposus can leak into the foraminal spaces, causing irritation of nerve roots and foraminal stenosis.

[0003] Treatments such as discectomy, laminectomy, laminotomy and/or spine fusion procedures represent state of the art surgical treatment for disc problems. Typically, the goal of these treatments is to relieve pressure on the neural elements by eliminating the material causing stenosis or irritation of the neural elements. However, discectomy when performed alone can result in significant loss of disc height and frequently provides only temporary pain relief. Laminectomy/laminotomy procedures also provide only temporary relief by opening up the spinal canal and decompressing the spinal cord, which is susceptible to restenosis due to scar tissue formation at the operative site. Spine fusion is considered by some to be a last resort, "most" invasive procedure that eliminates the flexibility of the motion segment and usually involves permanent hardware implantation. Furthermore, fusing spinal segments has been linked to adjacent level disc degeneration. All of these techniques have the disadvantage that they require surgical intervention to carry out the treatment.

[0004] Percutaneous microdiscectomy has been suggested as a minimally invasive discectomy procedure but still carries the disadvantage of causing disc height loss. Chemonucleolysis has been used clinically for decades and relieves pressure on a disc herniation by breaking down the nucleus pulposus. In essence, chemonucleolysis is a chemical discectomy. Because the goal of this treatment is to basically digest the nucleus, the consequent reduction in viscosity of the nucleus pulposus makes it more susceptible to leakage. In addition, this procedure appears to be associated with a 1% incidence

of anaphylaxis which has caused patient deaths. Furthermore, the procedure is known to also cause disc height loss.

[0005] Because of the drawbacks associated with the conventional procedures, newer procedures have been developed with an aim towards relieving back pain without requiring invasive surgery and without reducing disc height and providing a longer-lasting therapeutic effect.

[0006] Injecting curable or hardening materials into the disc following discectomy has been suggested in order to provide a filler material for the space left by removal of the nucleus and/or annular defect: US-6206921 (Guagliano) discloses a method of first removing the nucleus pulposus and/or herniated portion of the annulus fibrosis, then injecting a heated, resilient, natural rubber material that hardens upon cooling. US-6187048 (Milner) discloses an *in situ* polymerisable nucleus pulposus replacement material that may be enclosed by an impermeable container to prevent leakage. However, these materials may be susceptible to leakage out of the nucleus pulposus if no balloon or sheath has been formed around the material, particularly if the annulus fibrosis has not been adequately repaired. Furthermore, the implant may be subjected to repeated loads exceeding its strength over the lifetime it is expected to function in the patient. The potential consequence of failure is generation of foreign particulate, which has been linked to osteolysis and chronic foreign body reactions.

[0007] Other treatment options, which do not require discectomy or nucleotomy, have also been explored. US-6126682 (Sharkey) discloses a method of treating annular fissures by delivering energy and/or materials to localized places near the inner wall of the annulus fibrosus, particularly at the posterior margins, using a functional element. Heating the disc has the potential to "weld" defects and/or shrink disc tissues. However, the mechanism of heating the disc to weld defects is not well understood and may cause secondary problems such as tissue necrosis and nerve root damage. Sharkey also discloses delivering dissolved collagen, adhesives, cements or hydrogels to seal fissures in the annulus fibrosus using the surgical instrument and functional element. However, this delivery is restricted to local points along the inner wall of the annulus fibrosus for treating annular fissures.

[0008] Sharkey does not disclose providing a crosslinking agent in an amount effective to cause the crosslinking of any native molecular proteins of the disc, nor does Sharkey disclose depositing a sealant material into the centre of the nucleus pulposus portion of the disc.

[0009] WO-00/62832 (Haldimann) discloses an *in situ* curable sealant material that repairs defects in the disc annulus to prevent leakage of nucleus pulposus material. In some embodiments, Haldimann discloses that the sealant material is made of two precursor components: a buffered protein solution (including collagen) and a bi-functional crosslinking agent (including PEG with an activated terminal group). Typically, this injectable material

adheres to the surrounding tissues by mechanical interlocking. In some embodiments, Haldiman discloses that covalent bonds are formed between the preferred hydrogel bio-compatible material and the surrounding annulus fibrosus tissue to further increase and secure the attachment of the sealant to the annulus fibrosus tissue in the proximity to the defect in the annulus fibrosus. There is also disclosed a method of adding "artificial nucleus pulposus material" to achieve a volume comparable to a normal nucleus pulposus followed by sealing the annulus.

[0010] Haldiman does not disclose providing the crosslinking agent in an amount effective to cause the crosslinking of any of the native molecular proteins of the disc. Haldiman does not disclose depositing the sealant material into the nucleus pulposus.

[0011] WO-01/70151 (Aksan) discloses a method of strengthening and stabilizing collagenous tissues comprising the steps of heating to shrink the collagen followed by crosslinking with a non-toxic agent. The treatment is mainly focussed on glenohumeral instability and loose skin problems, but application of capsular shift procedures used to repair injuries of the spine is also mentioned. However, the crosslinking treatment always follows a thermal shrinkage step in the disclosed procedure. Thermal shrinkage is very difficult to achieve in the intervertebral disc beyond a local region without inducing damaging effects and is likely to cause a highly nonuniform tissue morphology. The crosslinking described is focussed on collagen molecules, which exist in relatively small proportions in the nucleus pulposus of the spine (about 5%).

[0012] Aksan does not specifically disclose injecting the crosslinking agent into the intervertebral disc portion of the spine. Aksan does not disclose any method of crosslinking an untreated protein component of the disc.

[0013] US-4931546 (Tardy) discloses a method for crosslinking collagen comprising exposing the collagen to a solution of periodic acid or a periodate, then allowing spontaneous crosslinking to occur from the aldehyde groups formed during exposure. Similarly, US-5972385 (Liu) discloses a method of oxidizing polysaccharides, then reacting the oxidized product with collagen and adding a growth factor, and discloses application of material so formed in spinal fusion augmentation. Neither Tardy nor Liu describes *in situ* crosslinking of native living tissues, particularly in the spine or intervertebral disc. WO-03/020031 provides a method of improving the resistance of collagenous tissue to mechanical degradation. The method comprises the steps of contacting at least a portion of a collagenous tissue with an effective amount of a crosslinking reagent.

[0014] Accordingly, there is a need for a minimally invasive method of treating pathological intervertebral discs that relieves back pain and encourages long-term disc stability and pain prevention by maintaining disc height, preventing nucleus leakage posteriorly, relieving pressure on a disc herniation, and inducing less alteration

of the normal spine biomechanics.

[0015] In accordance with the present invention, there is provided a method of manufacturing a medical composition for the treatment of a pathologic intervertebral disc wherein a crosslinking agent is delivered to the disc in an amount sufficient to cause the chemical crosslinking of at least a portion of the unmodified native proteins present in the disc. The crosslinking stabilizes and stiffens the disc structure, which has the therapeutic effect of relieving pressure on neural elements such as the spinal cord and the exiting nerve roots. The stabilization also prevents prolapse of the nucleus material, thereby preventing foraminal stenosis and loss of disc height. The invention further provides a least-invasive medical treatment for injured and/or degenerated intervertebral discs that will hopefully maintain most of the flexibility and functional biomechanics of the normal disc and prolong the need for surgical intervention.

[0016] The present invention involves crosslinking the native molecular components of the intervertebral disc, rather than removing or dissolving them. The potential effects of crosslinking are multi-fold, including altering the biomechanical nature of the nucleus pulposus from a viscous gel to a viscoelastic solid, thereby preventing prolapse into the spinal canal and reducing the tendency for excessive bulging of the annulus fibrosis, which are primary suspects for causing low back pain and sciatica. Crosslinking also inhibits the degradation of the disc by providing stable, durable chemical bonds, which can help maintain disc height and prevent excessive motion of the disc level, again preventing painful pinching of the nerves and rupture of the annular fibres. The present invention can be performed as an outpatient procedure and does not require surgical intervention, and so is particularly useful as a minimally invasive, early intervention strategy.

[0017] Therefore, in accordance with the present invention, there is provided a method of manufacturing a medical composition for the treatment of a living being an intervertebral disc having a nucleus pulposus, comprising the step of injecting a crosslinking agent into the nucleus pulposus.

[0018] For the purposes of the present invention, a "native protein" is any protein possessing any native elements. Accordingly, a native protein may have a synthetic functional group produced by reaction with a foreign agent and still be considered a native protein. An "unmodified protein" is a protein which has not been subjected to heat in an amount sufficient to shrink the collagen therein.

[0019] The intervertebral disc comprises three major components: 1) the nucleus pulposus, 2) the annulus fibrosus, and 3) a pair of cartilaginous endplates. The present invention may be practised upon any of these sites, alone or in any combination.

[0020] Preferably, the nucleus pulposus portion of the intervertebral disc is selected as the target site for the chemical crosslinking of the proteins therein. Treating

the nucleus pulposus with the method of the present invention can stiffen the nucleus pulposus (thereby reducing undesired mobility), and prevent native material within the nucleus pulposus from leaking out. In some embodiments, the crosslinking agent is injected only into the nucleus pulposus. When the crosslinking agent is injected into the nucleus pulposus, it is preferred that the agent be injected into the centre of the nucleus pulposus.

[0021] In some preferred embodiments, both the nucleus pulposus and the annulus fibrosis may be treated with the same injection of crosslinking agent. Still more preferably, the injection causes not only the crosslinking of substantially the entire bulk of the nucleus pulposus, but also the crosslinking of the periphery of the nucleus pulposus to the inner wall of the annulus fibrosus. When this embodiment is practised, it is preferred that the agent be injected only into (and preferably into the centre of) the nucleus pulposus, and that light exercise be performed by the patient in order to disperse the agent to the periphery of the nucleus pulposus.

[0022] In other preferred embodiments, only the annulus fibrosis is treated. Treating the annulus fibrosus with the method of the present invention can have the effect of binding a tear in the annulus fibrosus. When this embodiment is practised, it is preferred that the agent be injected into the defect produced by the tear.

[0023] In some procedures, compositions of the present invention may be first injected into a first site in the disc, and then injected into a second site in the same disc. For example, a probe can be first manoeuvred into the disc and positioned so that a composition of the present invention may be first delivered only into the nucleus pulposus portion of the disc. The probe can then be manoeuvred again within the disc and positioned so that the same (or a different) composition of the present invention may be delivered to a defect in the annulus fibrosus.

[0024] In some patients having a disc characterized by advanced degeneration, the line of demarcation between the annulus fibrosus and the nucleus pulposus becomes unclear. Accordingly, in these cases, the crosslinking agent is preferably injected into the centre of the disc.

[0025] The nucleus pulposus typically contains more than 80 volume percent (vol%) water (depending on age and condition). The protein content of the nucleus pulposus typically comprises approximately 50 weight percent (wt%) proteoglycans, 20 wt% collagen (mainly Type II collagen), and other small proteins such as fibronectin, thrombospondin, and elastin. The water and proteoglycan content of the nucleus pulposus generally decreases with age and onset of pathological changes. Hence, they are expected to be present in lower amounts in the intervertebral discs in patients that are candidates for the method of this invention.

[0026] The annulus fibrosis is generally slightly less hydrated than the nucleus pulposus and its protein content comprises about 15 wt% proteoglycan and 70 wt%

collagen (mainly Type I collagen). The annulus fibrosis may also lose water with age and disease, but generally experiences more structural changes, such as tearing and formation of thick bundles, than biochemical changes.

[0027] The cartilaginous endplate is a thin layer of hyaline cartilage similar to articular cartilage and dry weight is composed of mainly Type II collagen.

[0028] When the nucleus pulposus site is so selected, it is preferred that the crosslinking agent be selected so that it effectively causes the crosslinking of at least the proteoglycan protein component thereof (as it is the predominant protein in nucleus pulposus). It is more preferred that the crosslinking agent be selected so that it effectively causes the crosslinking of both the proteoglycan and collagen protein components thereof (as collagen is the second most predominant protein in nucleus pulposus). However, in some embodiments, the crosslinking agent is selected so that it effectively causes the cross linking of the collagen protein component thereof. In other embodiments, the crosslinking agent be selected so that it effectively causes the crosslinking of essentially all the protein components of the nucleus pulposus. When the annulus fibrosus site is so selected, it is preferred that the crosslinking agent be selected so that it effectively causes the cross linking of at least the collagen protein component thereof (as it is the predominant protein in annulus fibrosus). It is more preferred that the crosslinking agent be selected so that it effectively causes the crosslinking of both the proteoglycan and collagen protein components thereof (as proteoglycan is the second most predominant protein in the annulus fibrosis). However, in some embodiments, the crosslinking agent is selected so that it effectively causes the crosslinking of the proteoglycan protein component of the annulus fibrosus. In other embodiments, the crosslinking agent is selected so that it effectively causes the crosslinking of essentially all the protein components present at the defect of the annulus fibrosus.

[0029] Chemical crosslinking of the selected molecular components can be accomplished using a variety of methods, including both direct and indirect crosslinking processes. Typically, crosslinking of proteins is accomplished when an aldehyde functional group reacts with an amino acid group to form a bond between them. In some embodiments of the present invention involving aldehyde and amino acid functional groups, the aldehyde functional group may be either synthesized upon a native protein or provided by a foreign agent, while the amino acid functional group is either present upon a native protein or provided by a foreign agent, provided that at least one of the functional groups is present on a native protein.

[0030] For the purposes of the present invention, a crosslinking agent may "cause" the crosslinking of proteins by methods including but not limited to:

(a) directly chemically bridging two functional groups from two different protein molecules ("inter-protein

direct crosslinking");

(b) directly chemically bridging two functional groups from the same protein molecule ("intra-protein direct crosslinking");

(c) reacting with a first protein molecule to form a synthetic functional group on a first protein molecule (typically an aldehyde) which in turn reacts with a second functional group (typically an amino acid group) on a second protein molecule ("inter-protein indirect crosslinking"); or

(d) reacting with a protein molecule to form a synthetic functional group on the protein molecule (typically an aldehyde) which in turn reacts with a second functional group (typically an amino acid group) on the same protein (intra-protein indirect crosslinking).

[0031] Accordingly, in some embodiments, the in-situ crosslinking of the native proteins is accomplished by crosslinking a first synthetic functional group and a second functional group within a single native protein molecule. In some embodiments, the single native protein molecule is a proteoglycan, while in others the single native protein molecule is collagen. In general, aldehyde groups do typically not exist on native proteins. Accordingly, they must be provided as either a synthetic functional group (e.g., by using an oxidizing agent upon a protein) upon a native protein, or as a functional group of a foreign agent.

[0032] In other embodiments, the in-situ crosslinking of the native proteins is accomplished by crosslinking a first functional group of a first protein molecule with a second functional group of a second protein molecule. In some embodiments, the first protein molecule is the same type as the second protein molecule. In some cases thereof, the first and second protein molecules are Type I collagen, while in others the first and second protein molecules are Type II collagen, and in still others the first and second protein molecules are a type of proteoglycan. In some embodiments, the first protein molecule is a different type than the second protein molecule. In some embodiments thereof, the first protein molecule is a type of collagen and the second protein molecule is a proteoglycan. In other embodiments thereof, the first protein molecule is Type I collagen and the second protein molecule is Type II collagen. In other embodiments thereof, the first protein molecule is a glycosaminoglycan and the second protein molecule is Type II collagen.

[0033] Direct crosslinking can be used in accordance with the present invention, and typically involves using the crosslinking agent as a bridge to chemically connect one amino acid group on one protein molecule to another amino acid group on the same or different protein molecule. These agents are called bifunctional agents. In some preferred embodiments, the crosslinking agent comprises a pair of functional groups that react with amino acid groups on the native proteins to be linked. Preferably, these functional groups are aldehydes.

[0034] Direct crosslinking can be accomplished in ei-

ther conventional one step or multistep procedures. Conventional methods of direct crosslinking are described by Khor (Biomaterials 18:95-105, 1997), which discloses methods for crosslinking collagenous tissues to improve durability, particularly transplant tissues from xenogeneic or allogeneic sources. In some embodiments of the present invention, direct crosslinking is accomplished in a one-step reaction, preferably by using a bifunctional agent. In some embodiments, the bifunctional agent is selected from the group consisting of dialdehydes, polyepoxy compounds and diisocyanates. One more preferred bifunctional agent used in accordance with the present invention is glutaraldehyde.

[0035] Conventional, multistep, direct, crosslinking reactions are also described by Khor. In some embodiments using multistep reactions, the bifunctional crosslinking agent is selected from the group consisting of acyl azide and carbodiimides.

[0036] Pathak et al. (Soc for Biomaterials 27th Annual Meeting Transactions p. 130, 2001) describe an alternative to glutaraldehyde fixation of bovine pericardium using bis-(sulphosuccinimidyl suberate) as the bifunctional agent. It is believed that bis(sulphosuccinimidyl suberate) may be less toxic than glutaraldehyde and is better resistant to calcification.

[0037] Crosslinking agents can also be made by attaching functional groups to synthetic polymers, which may improve biocompatibility. One particular example is functionally activating poly(ethylene glycol) with aldehyde groups to manufacture an agent that will directly crosslink tissues in a manner similar to glutaraldehyde and formaldehyde.

[0038] Preferably, the direct crosslinking agent of the present invention has a molecular weight of no more than 1 million Daltons. Above this preferred value, the crosslinking agent may be insoluble in water and may be very difficult to inject and disperse into the disc tissues. More preferably, the crosslinking agent has a molecular weight of between about 100 Daltons and about 100,000 Daltons. When the molecular weight of the agent is below about 100 Daltons, the agent may too easily diffuse into bodily tissues outside of the intervertebral disc. When the molecular weight of the agent is above about 100,000 Daltons, the agent may not disperse adequately within the disc tissues to cause uniform crosslinking of native molecules.

[0039] One preferred embodiment of this invention involves the direct, one step, aqueous reaction of a water-soluble, bifunctional crosslinking agent with at least a portion of the native proteins of the intervertebral disc. Preferred crosslinking agents for this method include glutaraldehyde, bis(sulphosuccinimidyl suberate), polyepoxy compounds and bifunctionally activated synthetic polymers such as poly(ethylene glycol) dialdehyde. Preferably, the agent is diluted in a pH buffered physiological saline prior to administration. A buffered pH environment is desirable to maintain favourable reaction conditions during crosslinking.

[0040] Glutaraldehyde is particularly preferred as a crosslinking agent due to its medical history of use with biological transplant tissues and injectable adhesives. Preferably, the crosslinking agent (which is preferably glutaraldehyde) is delivered to the disc in a concentration of between approximately 0.1 and 20 volume percent (vol%), more preferably between 1 and 10 vol% in saline buffered to a pH of approximately 6.5 to 8.0, more preferably between approximately 7.0 to 7.5.

[0041] Another method of causing the crosslinking of native intervertebral disc molecular components is to chemically react target portions of native proteins (such as native collagen and/or native proteoglycan proteins) such that synthetic functional groups (such as aldehydes) are created directly on the native proteins. Crosslinking then preferably occurs between the synthetic functional groups (such as aldehyde groups) of the reacted native protein and an unreacted functional group (such as an amino acid group) located on either the same native protein or another molecule. Modification of the native component to form a functional group such as an aldehyde can be achieved using enzymatic oxidizing agents, and are preferably selected from the group consisting of lysine oxidase, transglutaminase, and multi-copper oxidases. Proteoglycans contain polysaccharide regions that may be modified to form aldehyde functional groups. This modification of proteoglycans may be accomplished by using either enzymatic or non-enzymatic agents. Examples of enzymatic polysaccharide oxidizing agents include catechol oxidase and tyrosinase. Examples of non-enzymatic polysaccharide oxidizing agents include periodate ions (periodic acid, sodium and potassium periodate), nitroprusside ions (sodium nitroprusside) and hydrogen peroxide.

[0042] In a preferred embodiment of this invention, a non-enzymatic polysaccharide oxidizing agent is injected into the nucleus pulposus of a pathological intervertebral disc. Because the dry weight component of the nucleus pulposus is rich in proteoglycans, there are numerous sites that can be oxidized to form functional aldehydes. Subsequently, the aldehydes can react with amino acid regions of both native collagens and native proteoglycans to form crosslinks.

[0043] Chemical modification of proteoglycans, particularly the sulphated proteoglycans, in the nucleus pulposus can elicit the added benefit of reducing the swelling pressure in the nucleus, thereby reducing both the potential for exuding out of the disc and the tendency for the nucleus pulposus to cause bulging of the annulus. This is one proposed mechanism for the effectiveness of chemonucleolysis in reducing pain in properly selected patients (*Kato et al., Spine 17:934-939, 1992*). Furthermore, this mechanism is the basis for clinical experiments conducted with aprotinin, a protease inhibitor that forms strong complexes with sulphated glycosaminoglycans (*Kraemer et al., Spine 7:73-74, 1982*).

[0044] Preferably, the indirect crosslinking agent of the present invention has a relatively low molecular weight,

is substantially completely reacted in the crosslinking process, and forms by-products (such as gases and water) which can relatively easily exit the reaction site.

[0045] Although the agents used in the disclosed invention are preferably non-toxic at the concentrations employed for treatment, it may be desirable to substantially inactivate any residual crosslinking agent with an inactivating agent once adequate crosslinking has been achieved in order to reduce any toxic potential the crosslinking agent may still possess. For example, a diluted solution of glycine will inactivate unreacted glutaraldehyde as disclosed in WO-01/70151). Because the inactivating agent can react with the crosslinking agent, in preferred embodiments, the crosslinking agent is provided in first sterile container and the inactivating agent is provided in a second sterile container.

[0046] In certain crosslinking procedures, the reaction is reversible, particularly if there is a dramatic change in pH. For these reversible reactions, it may be preferable to add a stabilizing agent once the crosslinking has been achieved. For example, the reaction of aldehyde functional groups with proteins generally forms what is known as a Schiff base, which may be a reversible reaction (with the exception of glutaraldehyde, which may undergo an irreversible reaction with proteins). In these cases where reverse reactions are possible, it may be preferable to include a later step of adding a stabilizing agent that substantially prevents the reversal of the crosslinking reaction. Preferred stabilizing agents comprise boron compounds. More preferred stabilizing agents are selected from the group consisting of sodium borohydride, sodium cyanoborohydride or pyridine borane. Pyridine borane is a more preferred agent for this invention due to its relatively higher biocompatibility. Because the stabilizing agent can react with the crosslinking agent, in preferred embodiments, the crosslinking agent is provided in a first sterile container and the stabilizing agent is provided in a second sterile container.

[0047] In some embodiments, one or more of the compounds selected from the group consisting of the crosslinking agent, the inactivating agent and the stabilizing agent is delivered (preferably, separately) to the disc in a buffered saline solution capable of controlling pH during the crosslinking reaction. Preferably, the solution is buffered to a pH of approximately 6.5 to 8.0, more preferably between approximately 7.0 to 7.5.

[0048] In some embodiments, one or more of the compounds selected from the group consisting of the crosslinking agent, the inactivating agent and the stabilizing agent is delivered (preferably, separately) to the disc in a composition further comprising a radio-opaque contrast medium present in an amount sufficient to monitor the flow of the composition through fluoroscopy. In some embodiments, the radio-opaque contrast medium comprises iodine. In some embodiments, the radio-opaque contrast medium is an iodine-containing dye. In some embodiments, the radio-opaque contrast medium comprises a compound selected from the group consist-

ing of barium-containing compounds (such as barium sulphate), zirconia and tantalum, is preferably a barium-containing compound, and more preferably is barium sulphate.

[0049] In preferred embodiments, the compound is delivered in a buffered saline solution containing the radio-opaque contrast medium. In more preferred embodiments, each compound used in the procedure is delivered in a buffered saline solution containing the radio-opaque contrast medium.

[0050] When certain embodiments of the present invention are practised, there is produced a composition formed within an intervertebral disc having a level of naturally crosslinked proteins, the composition comprising a crosslinked structure comprising proteins which are native to the natural intervertebral disc, wherein the crosslinked structure has a degree of crosslinking which is higher than the unmodified level of naturally crosslinked proteins. Preferably, the naturally crosslinked proteins are unmodified.

[0051] In some embodiments, the crosslinked structure further comprises a direct cross linking agent, preferably glutaraldehyde. In others, the crosslinked structure has been crosslinked using an indirect crosslinking agent which is not incorporated into the crosslinked structure. In preferred embodiments, the disc further comprises an annulus fibrosus having an inner wall, and wherein the crosslinked structure includes the inner wall of the annulus fibrosus. In others, the crosslinked structure is present essentially within the nucleus pulposus. In others, the crosslinked structure is present essentially throughout the entire disc.

[0052] In a preferred embodiment of the invention, the agents and materials to be delivered to the intervertebral disc are injected percutaneously under fluoroscopic control using a syringe and appropriate gauge needle, for example 25G. Such a minimally invasive procedure is highly desirable for minimizing damage to musculoskeletal structures and can be performed using an outpatient procedure. Although this injection can be delivered from any approach to the disc, it is preferable to use a posterior or posterolateral approach such that the needle is required to pass through a shortest distance before reaching the disc without penetrating major vascular or neural structures. Preferably, the agents and materials of this invention are injected into the centre of the nucleus pulposus of the disc such that the material can then disperse radially into the remainder of the nucleus pulposus and/or remainder of the disc.

[0053] The volume of diluted crosslinking solution injected into the disc is preferably between approximately 0.1 and 10 ml, more preferably between approximately 1 and 5 ml. This ensures that adequate crosslinking agent is delivered to the disc yet does not produce high pressures in the disc, potentially causing failure of the disc and extruding of crosslinking agent and disc material.

[0054] In another preferred embodiment, light exercising is used as an adjunct to the procedure in order to aid

in the dispersing of agents and materials within the disc and to ensure complete reaction of the functional materials injected and/or generated. Examples of light exercise include limited left and right lateral bending, flexion and extension, and torso twists (axial rotation). Preferably, the light exercising is performed after each step of the treatment to disperse each agent or material prior to delivering a subsequent material.

[0055] As noted above, it is desirable to provide the different compounds used in the present invention in separate sterile containers in order to avoid undesirable reactions between them prior to their injection into the disc.

[0056] Therefore, in accordance with the present invention, there is provided a kit for injecting therapeutic solutions into an intervertebral disc having native proteins, consisting of:

- (a) a first container having a sterile inner surface and containing a first compound, in which the first compound is a crosslinking agent present in an effective amount for cross linking at least a portion of the native proteins, and
- (b) a second container having a sterile inner surface and containing a second different compound,

in which the second compound is selected from the group consisting of:

- (i) an inactivating agent, and
- (ii) a stabilizing agent

[0057] In preferred embodiments, at least one container containing a compound further contains a buffered saline solution, and preferably further contains a radio-opaque contrast medium. In more preferred embodiments, each provided container containing a compound further contains a buffered saline solution, and preferably further contains a radio-opaque contrast medium.

[0058] In some preferred kit embodiments, the crosslinking agent is a direct crosslinking agent (such as glutaraldehyde). In others, the crosslinking agent is an indirect cross linking agent (such as sodium periodate).

[0059] In some embodiments, the kit further comprises first and second sterile syringes for separately injecting the compounds. In other embodiments, a third syringe is also provided. In some embodiments, the containers of the kit are provided in a case. Likewise the syringes of the kit are provided in the case.

REFERENCE EXAMPLE 1: Biomechanical Testing of Cadaveric Functional Spine Units after Crosslinking Treatment

[0060] In a prophetic experiment, four human cadaveric lumbar spine segments (L1 - L5) are tested biomechanically to determine range-of-motion (ROM) in flexion-extension, lateral bending, axial torsion and pure compression to establish a baseline. Three crosslinking

solutions plus one control solution are prepared: 1) 10% w/v glutaraldehyde in 0.1M phosphate buffered saline (PBS) with pH 7.4; 2) 10% w/v bis(sulphosuccinimidyl suberate) in PBS; 3) 10% sodium periodate in PBS; 4) PBS alone. For a given treatment, 2 ml of solution is injected into the centre of one of the four intervertebral discs of the cadaveric lumbar spine using a 5 ml syringe and 25G needle. For each spine segment, all treatments are applied, one to each level.

[0061] Following the injections, the spine segments are subjected to simulated light exercise, i.e. flexion-extension, lateral bending and axial rotation. These exercises are repeated at various times during the course of the experiment. After 2 hours and 24 hours, the biomechanical range-of-motion (ROM) testing is repeated to measure the effect of crosslinking on each motion segment.

[0062] The range of motion testing should indicate that the stiffness of the segments significantly increased over that of a normal untreated disc.

REFERENCE EXAMPLE 2: Outpatient Procedure for In Situ Crosslinking Treatment of the Intervertebral Disc

[0063] After complaining of low back and leg pain, a patient is referred to a spine specialist. Using x-rays and MRI, the physician determines that the pain is being caused by a bulging intervertebral disc with loss of disc height. The recommended treatment is restoration of disc height with an injection of soluble Type I atelocollagen followed by crosslinking treatment with 10% glutaraldehyde.

[0064] In the first outpatient procedure, 2 ml of atelopeptide Type I collagen solution is injected percutaneously into the centre of the intervertebral disc. The patient then follows a prescribed light exercise regimen of limited right and left lateral bending, flexion and extension, and torsional twisting and told to refrain from lifting heavy objects and engaging in high impact exercises.

[0065] The second outpatient procedure is performed on the following day. In this procedure, 2 ml of 10% glutaraldehyde solution in 0.1 M phosphate buffered saline (pH 7.4) is injected percutaneously into the centre of the intervertebral disc. Again, the patient then follows a prescribed light exercise regimen of limited right and left lateral bending, flexion and extension, and torsional twisting and told to refrain from lifting heavy objects and engaging in high impact exercises for at least two days.

Claims

1. Use of (a) a crosslinking agent, and (b) an inactivating agent Capable of inactivating any residual crosslinking agent or a stabilising agent capable of preventing the reversal of the crosslinking reactions, in the manufacture of a composition for the treatment of an intervertebral disc which is affected by any of

disc herniation, rupture of the annulus, prolapse of the nucleus pulposus, mechanical instability of the disc, and dehydration of the disc, where disc height is maintained, leakage of the nucleus is prevented posteriorly, pressure on a disc herniation is relieved, and less alteration to normal spine biomechanics is induced, in which composition is presented in a kit which comprises first and second containers, each having sterile inner surfaces, for containing the crosslinking agent and the inactivating agent or the stabilising agent respectively, and in which the composition does not contain supplemental protein.

2. The use of agents in the manufacture of a kit, as claimed in claim 1, in which the composition with which the disc is to be treated includes a buffered saline solution and a radio-opaque contrast medium.
3. The use of agents in the manufacture of a kit, as claimed in claim 1, in which the crosslinking agent is present in its container in a concentration of between 0.1 and 20 volume percent, preferably between 1 and 10 volume percent.
4. The use of agents in the manufacture of a kit, as claimed in claim 1, in which the crosslinking agent is glutaraldehyde.

Patentansprüche

1. Verwendung von (a) einem Vernetzungsagens und (b) einem Inaktivierungsagens, das fähig ist zum Inaktivieren von jeglichem restlichen Vernetzungsagens, oder einem Stabilisierungsagens, das fähig ist zum Vermeiden der Umkehr der Vernetzungsreaktion, bei der Herstellung einer Zusammensetzung für die Behandlung einer Bandscheibe, die durch irgendeines von Scheibeneinklemmung, Ruptur des Anulus, Prolaps des Nukleus pulposus, mechanischer Instabilität der Scheibe und Dehydratisierung der Scheibe betroffen ist, wobei eine Scheibenhöhe bewahrt wird, Auslaufen des Nukleus posterior vermieden wird, Druck auf eine Scheibeneinklemmung abgebaut wird und weniger Umbildung zu normaler Wirbelbiomechanik induziert wird, bei welcher die Zusammensetzung in einem Kit dargeboten wird, der erste und zweite Behälter umfaßt, jeweils mit sterilen inneren Oberflächen, zur Aufnahme des Vernetzungsagens bzw. des Inaktivierungsagens oder des Stabilisierungsagens, und bei welcher die Zusammensetzung kein ergänzendes Protein enthält.
2. Verwendung von Agentien bei der Herstellung eines Kits nach Anspruch 1, bei welcher die Zusammensetzung, mit der die Scheibe zu behandeln ist, eine gepufferte Salzlösung und ein Röntgenstrahlen undurchlässiges Kontrastmedium einschließt.

3. Verwendung von Agentien bei der Herstellung eines Kits nach Anspruch 1, bei welcher das Vernetzungsmittel in seinem Behälter in einer Konzentration zwischen 0,1 und 20 Vol-%, bevorzugt zwischen 1 und 10 Vol-% vorliegt. 5
4. Verwendung von Agentien bei der Herstellung eines Kits nach Anspruch 1, bei welcher das Vernetzungsmittel Glutaraldehyd ist. 10

Revendications

1. Utilisation (a) d'un agent réticulant, et (b) d'un agent inactivant capable d'inactiver tout agent réticulant résiduel ou d'un agent stabilisant capable d'empêcher l'inversion de la réaction de réticulation, dans la fabrication d'une composition pour le traitement d'un disque intervertébral qui est affecté par une hernie discale, une rupture de l'anneau, un prolapsus du nucleus pulposus, une instabilité mécanique du disque ou déshydratation du disque, où la hauteur discale est maintenue, la fuite du nucleus est évitée postérieurement, la pression sur une hernie discale est soulagée, et une moindre altération de la biochimie spinale normale est induite, la composition étant présentée sous la forme d'un kit qui comprend des premier et deuxième récipients, chacun ayant des surfaces intérieures stériles, pour contenir respectivement l'agent réticulant et l'agent inactivant ou l'agent stabilisant, et la composition ne contenant pas de protéine supplémentaire. 15 20 25 30
2. Utilisation d'agents dans la fabrication d'un kit, selon la revendication 1, dans laquelle la composition avec laquelle le disque doit être traité comprend une solution saline tamponnée et une substance de contraste radio-opaque. 35
3. Utilisation d'agents dans la fabrication d'un kit, selon la revendication 1, dans laquelle l'agent réticulant est présent dans son récipient sous la forme d'une concentration entre 0,1 et 20 pour cent en volume, de préférence entre 1 et 10 pour cent en volume. 40 45
4. Utilisation d'agents dans la fabrication d'un kit, selon la revendication 1, dans laquelle l'agent réticulant est du glutaraldéhyde. 50 55



(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
24.09.2003 Bulletin 2003/39

(51) Int Cl.7: **A61L 27/50**

(21) Application number: **03251687.4**

(22) Date of filing: **19.03.2003**

(84) Designated Contracting States:
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IT LI LU MC NL PT RO SE SI SK TR
Designated Extension States:
AL LT LV MK

(30) Priority: **19.03.2002 US 102075**

(71) Applicant: **DePuy AcroMed, Inc.**
Raynham, MA 02767 (US)

(72) Inventors:
• **Slivka, Michael Andrew**
Taunton, MA 02780 (US)
• **Serhan, Hassan**
South Easton, MA 02375 (US)

(74) Representative: **Belcher, Simon James**
Urquhart-Dykes & Lord
Tower House
Merrion Way
Leeds LS2 8PA (GB)

(54) **Intervertebral disk treatment using a crosslinking agent**

(57) Compositions for treating pathological intervertebral discs include an agent that causes chemical crosslinking of the native molecular components of the disc. Supplemental materials which are susceptible to

crosslinking by the aforementioned agent are optionally delivered to the disc in order to increase and to maintain disc height.

Description

[0001] This invention relates to a kit for intervertebral disc treatment.

[0002] The intervertebral disc contains three major components: a nucleus pulposus (a fluid-like component comprising proteoglycans and collagen), an annulus fibrosis (a flexible, collagen-based ring surrounding the nucleus pulposus) and a pair of cartilaginous endplates which help enclose the nucleus pulposus within the annulus fibrosus. A normal, healthy nucleus pulposus acts much like a pressurized fluid by transferring and distributing compressive load to the annulus fibrosis, thereby causing a slight expansion of the annulus fibrosus. However, injury and/or degeneration of the intervertebral disc in the human spine can be caused by disc herniation, rupture of the annulus, prolapse of the nucleus pulposus, mechanical instability of the disc and/or dehydration of the disc, thereby leading to back pain. In addition, damage or degeneration of the annulus fibrosus in the form of a herniation, tear and/or crack reduces its ability to resist the tensile stresses conferred by the nucleus pulposus. Thus, the disc experiences excessive bulging that may result in spinal cord and/or nerve root impingement and subsequent back pain. Further, the nucleus pulposus can leak into the foraminal spaces, causing irritation of nerve roots and foraminal stenosis.

[0003] Treatments such as discectomy, laminectomy, laminotomy and/or spine fusion procedures represent state of the art surgical treatment for disc problems. Typically, the goal of these treatments is to relieve pressure on the neural elements by eliminating the material causing stenosis or irritation of the neural elements. However, discectomy when performed alone can result in significant loss of disc height and frequently provides only temporary pain relief. Laminectomy/laminotomy procedures also provide only temporary relief by opening up the spinal canal and decompressing the spinal cord, which is susceptible to restenosis due to scar tissue formation at the operative site. Spine fusion is considered by some to be a last resort, "most" invasive procedure that eliminates the flexibility of the motion segment and usually involves permanent hardware implantation. Furthermore, fusing spinal segments has been linked to adjacent level disc degeneration. All of these techniques have the disadvantage that they require surgical intervention to carry out the treatment.

[0004] Percutaneous microdiscectomy has been suggested as a minimally invasive discectomy procedure but still carries the disadvantage of causing disc height loss. Chemonucleolysis has been used clinically for decades and relieves pressure on a disc herniation by breaking down the nucleus pulposus. In essence, chemonucleolysis is a chemical discectomy. Because the goal of this treatment is to basically digest the nucleus, the consequent reduction in viscosity of the nucleus pulposus makes it more susceptible to leakage. In addition,

this procedure appears to be associated with a 1% incidence of anaphylaxis which has caused patient deaths. Furthermore, the procedure is known to also cause disc height loss.

[0005] Because of the drawbacks associated with the conventional procedures, newer procedures have been developed with an aim towards relieving back pain without requiring invasive surgery and without reducing disc height and providing a longer-lasting therapeutic effect.

[0006] Injecting curable or hardening materials into the disc following discectomy has been suggested in order to provide a filler material for the space left by removal of the nucleus and/or annular defect. US-6206921 (Guagliano) discloses a method of first removing the nucleus pulposus and/or herniated portion of the annulus fibrosis, then injecting a heated, resilient, natural rubber material that hardens upon cooling. US-6187048 (Milner) discloses an *in situ* polymerisable nucleus pulposus replacement material that may be enclosed by an impermeable container to prevent leakage. However, these materials may be susceptible to leakage out of the nucleus pulposus if no balloon or sheath has been formed around the material, particularly if the annulus fibrosis has not been adequately repaired. Furthermore, the implant may be subjected to repeated loads exceeding its strength over the lifetime it is expected to function in the patient. The potential consequence of failure is generation of foreign particulate, which has been linked to osteolysis and chronic foreign body reactions.

[0007] Other treatment options, which do not require discectomy or nucleotomy, have also been explored. US-6126682 (Sharkey) discloses a method of treating annular fissures by delivering energy and/or materials to localized places near the inner wall of the annulus fibrosus, particularly at the posterior margins, using a functional element. Heating the disc has the potential to "weld" defects and/or shrink disc tissues. However, the mechanism of heating the disc to weld defects is not well understood and may cause secondary problems such as tissue necrosis and nerve root damage. Sharkey also discloses delivering dissolved collagen, adhesives, cements or hydrogels to seal fissures in the annulus fibrosus using the surgical instrument and functional element. However, this delivery is restricted to local points along the inner wall of the annulus fibrosus for treating annular fissures.

[0008] Sharkey does not disclose providing a crosslinking agent in an amount effective to cause the crosslinking of any native molecular proteins of the disc, nor does Sharkey disclose depositing a sealant material into the centre of the nucleus pulposus portion of the disc.

[0009] WO-00/62832 (Haldimann) discloses an *in situ* curable sealant material that repairs defects in the disc annulus to prevent leakage of nucleus pulposus material. In some embodiments, Haldimann discloses that the sealant material is made of two precursor compo-

nents: a buffered protein solution (including collagen) and a bifunctional crosslinking agent (including PEG with an activated terminal group). Typically, this injectable material adheres to the surrounding tissues by mechanical interlocking. In some embodiments, Haldiman discloses that covalent bonds are formed between the preferred hydrogel bio-compatible material and the surrounding annulus fibrosus tissue to further increase and secure the attachment of the sealant to the annulus fibrosus tissue in the proximity to the defect in the annulus fibrosus. There is also disclosed a method of adding "artificial nucleus pulposus material" to achieve a volume comparable to a normal nucleus pulposus followed by sealing the annulus.

[0010] Haldiman does not disclose providing the crosslinking agent in an amount effective to cause the crosslinking of any of the native molecular proteins of the disc. Haldiman does not disclose depositing the sealant material into the nucleus pulposus.

[0011] WO-01/70151 (Aksan) discloses a method of strengthening and stabilizing collagenous tissues comprising the steps of heating to shrink the collagen followed by crosslinking with a non-toxic agent. The treatment is mainly focussed on glenohumeral instability and loose skin problems, but application of capsular shift procedures used to repair injuries of the spine is also mentioned. However, the crosslinking treatment always follows a thermal shrinkage step in the disclosed procedure. Thermal shrinkage is very difficult to achieve in the intervertebral disc beyond a local region without inducing damaging effects and is likely to cause a highly non-uniform tissue morphology. The crosslinking described is focussed on collagen molecules, which exist in relatively small proportions in the nucleus pulposus of the spine (about 5%).

[0012] Aksan does not specifically disclose injecting the crosslinking agent into the intervertebral disc portion of the spine. Aksan does not disclose any method of crosslinking an untreated protein component of the disc.

[0013] US-4931546 (Tardy) discloses a method for crosslinking collagen comprising exposing the collagen to a solution of periodic acid or a periodate, then allowing spontaneous crosslinking to occur from the aldehyde groups formed during exposure. Similarly, US-5972385 (Liu) discloses a method of oxidizing polysaccharides, then reacting the oxidized product with collagen and adding a growth factor, and discloses application of material so formed in spinal fusion augmentation.. Neither Tardy nor Liu describes *in situ* crosslinking of native living tissues, particularly in the spine or intervertebral disc.

[0014] Accordingly, there is a need for a minimally invasive method of treating pathological intervertebral discs that relieves back pain and encourages long-term disc stability and pain prevention by maintaining disc height, preventing nucleus leakage posteriorly, relieving pressure on a disc herniation, and inducing less alteration of the normal spine biomechanics.

[0015] In accordance with the present invention, there is provided a method of treating a pathologic intervertebral disc wherein a crosslinking agent is delivered to the disc in an amount sufficient to cause the chemical crosslinking of at least a portion of the unmodified native proteins present in the disc. The crosslinking stabilizes and stiffens the disc structure, which has the therapeutic effect of relieving pressure on neural elements such as the spinal cord and the exiting nerve roots. The stabilization also prevents prolapse of the nucleus material, thereby preventing foraminal stenosis and loss of disc height. The invention further provides a least-invasive medical treatment for injured and/or degenerated intervertebral discs that will hopefully maintain most of the flexibility and functional biomechanics of the normal disc and prolong the need for surgical intervention.

[0016] The present invention involves crosslinking the native molecular components of the intervertebral disc, rather than removing or dissolving them. The potential effects of crosslinking are multi-fold, including altering the biomechanical nature of the nucleus pulposus from a viscous gel to a viscoelastic solid, thereby preventing prolapse into the spinal canal and reducing the tendency for excessive bulging of the annulus fibrosis, which are primary suspects for causing low back pain and sciatica. Crosslinking also inhibits the degradation of the disc by providing stable, durable chemical bonds, which can help maintain disc height and prevent excessive motion of the disc level, again preventing painful pinching of the nerves and rupture of the annular fibres. The present invention can be performed as an outpatient procedure and does not require surgical intervention, and so is particularly useful as a minimally invasive, early intervention strategy.

[0017] Therefore, in accordance with the present invention, there is provided a method of treating in a living being an intervertebral disc having a nucleus pulposus, comprising the step of injecting a crosslinking agent into the nucleus pulposus.

[0018] Also in accordance with the present invention, there is provided method of treating in a living being an intervertebral disc having a nucleus pulposus, an annulus fibrosus, and native proteins, comprising the step of injecting an effective amount of a crosslinking agent into the intervertebral disc to cause *in situ* crosslinking of at least a portion of the native proteins present in the disc

[0019] For the purposes of the present invention, a "native protein" is any protein possessing any native elements. Accordingly, a native protein may have a synthetic functional group produced by reaction with a foreign agent and still be considered a native protein. An "unmodified protein" is a protein which has not been subjected to heat in an amount sufficient to shrink the collagen therein.

[0020] The intervertebral disc comprises three major components: 1) the nucleus pulposus, 2) the annulus fibrosus, and 3) a pair of cartilaginous endplates. The present invention may be practised upon any of these

sites, alone or in any combination.

[0021] Preferably, the nucleus pulposus portion of the intervertebral disc is selected as the target site for the chemical crosslinking of the proteins therein. Treating the nucleus pulposus with the method of the present invention can stiffen the nucleus pulposus (thereby reducing undesired mobility), and prevent native material within the nucleus pulposus from leaking out. In some embodiments, the crosslinking agent is injected only into the nucleus pulposus. When the crosslinking agent is injected into the nucleus pulposus, it is preferred that the agent be injected into the centre of the nucleus pulposus.

[0022] In some preferred embodiments, both the nucleus pulposus and the annulus fibrosis may be treated with the same injection of crosslinking agent. Still more preferably, the injection causes not only the crosslinking of substantially the entire bulk of the nucleus pulposus, but also the crosslinking of the periphery of the nucleus pulposus to the inner wall of the annulus fibrosus. When this embodiment is practised, it is preferred that the agent be injected only into (and preferably into the centre of) the nucleus pulposus, and that light exercise be performed by the patient in order to disperse the agent to the periphery of the nucleus pulposus.

[0023] In other preferred embodiments, only the annulus fibrosis is treated. Treating the annulus fibrosus with the method of the present invention can have the effect of binding a tear in the annulus fibrosus. When this embodiment is practised, it is preferred that the agent be injected into the defect produced by the tear.

[0024] In some procedures, compositions of the present invention may be first injected into a first site in the disc, and then injected into a second site in the same disc. For example, a probe can be first manoeuvred into the disc and positioned so that a composition of the present invention may be first delivered only into the nucleus pulposus portion of the disc. The probe can then be manoeuvred again within the disc and positioned so that the same (or a different) composition of the present invention may be delivered to a defect in the annulus fibrosus.

[0025] In some patients having a disc characterized by advanced degeneration, the line of demarcation between the annulus fibrosus and the nucleus pulposus becomes unclear. Accordingly, in these cases, the crosslinking agent is preferably injected into the centre of the disc.

[0026] The nucleus pulposus typically contains more than 80 volume percent (vol%) water (depending on age and condition). The protein content of the nucleus pulposus typically comprises approximately 50 weight percent (wt%) proteoglycans, 20 wt% collagen (mainly Type II collagen), and other small proteins such as fibronectin, thrombospondin, and elastin. The water and proteoglycan content of the nucleus pulposus generally decreases with age and onset of pathological changes. Hence, they are expected to be present in lower

amounts in the intervertebral discs in patients that are candidates for the method of this invention.

[0027] The annulus fibrosis is generally slightly less hydrated than the nucleus pulposus and its protein content comprises about 15 wt% proteoglycan and 70 wt% collagen (mainly Type I collagen). The annulus fibrosis may also lose water with age and disease, but generally experiences more structural changes, such as tearing and formation of thick bundles, than biochemical changes.

[0028] The cartilaginous endplate is a thin layer of hyaline cartilage similar to articular cartilage and dry weight is composed of mainly Type II collagen.

[0029] When the nucleus pulposus site is so selected, it is preferred that the crosslinking agent be selected so that it effectively causes the crosslinking of at least the proteoglycan protein component thereof (as it is the predominant protein in nucleus pulposus). It is more preferred that the crosslinking agent be selected so that it effectively causes the crosslinking of both the proteoglycan and collagen protein components thereof (as collagen is the second most predominant protein in nucleus pulposus). However, in some embodiments, the crosslinking agent is selected so that it effectively causes the cross linking of the collagen protein component thereof. In other embodiments, the crosslinking agent be selected so that it effectively causes the crosslinking of essentially all the protein components of the nucleus pulposus. When the annulus fibrosus site is so selected, it is preferred that the crosslinking agent be selected so that it effectively causes the cross linking of at least the collagen protein component thereof (as it is the predominant protein in annulus fibrosus). It is more preferred that the crosslinking agent be selected so that it effectively causes the crosslinking of both the proteoglycan and collagen protein components thereof (as proteoglycan is the second most predominant protein in the annulus fibrosis). However, in some embodiments, the crosslinking agent is selected so that it effectively causes the crosslinking of the proteoglycan protein component of the annulus fibrosus. In other embodiments, the crosslinking agent is selected so that it effectively causes the crosslinking of essentially all the protein components present at the defect of the annulus fibrosus.

[0030] Chemical crosslinking of the selected molecular components can be accomplished using a variety of methods, including both direct and indirect crosslinking processes. Typically, crosslinking of proteins is accomplished when an aldehyde functional group reacts with an amino acid group to form a bond between them. In some embodiments of the present invention involving aldehyde and amino acid functional groups, the aldehyde functional group may be either synthesized upon a native protein or provided by a foreign agent, while the amino acid functional group is either present upon a native protein or provided by a foreign agent, provided that at least one of the functional groups is present on a native protein.

[0031] For the purposes of the present invention, a crosslinking agent may "cause" the crosslinking of proteins by methods including but not limited to:

- (a) directly chemically bridging two functional groups from two different protein molecules ("inter-protein direct crosslinking");
- (b) directly chemically bridging two functional groups from the same protein molecule ("intra-protein direct crosslinking");
- (c) reacting with a first protein molecule to form a synthetic functional group on a first protein molecule (typically an aldehyde) which in turn reacts with a second functional group (typically an amino acid group) on a second protein molecule ("inter-protein indirect crosslinking"); or
- (d) reacting with a protein molecule to form a synthetic functional group on the protein molecule (typically an aldehyde) which in turn reacts with a second functional group (typically an amino acid group) on the same protein (intra-protein indirect crosslinking).

[0032] Accordingly, in some embodiments, the in-situ crosslinking of the native proteins is accomplished by crosslinking a first synthetic functional group and a second functional group within a single native protein molecule. In some embodiments, the single native protein molecule is a proteoglycan, while in others the single native protein molecule is collagen. In general, aldehyde groups do typically not exist on native proteins. Accordingly, they must be provided as either a synthetic functional group (e.g., by using an oxidizing agent upon a protein) upon a native protein, or as a functional group of a foreign agent.

[0033] In other embodiments, the in-situ crosslinking of the native proteins is accomplished by crosslinking a first functional group of a first protein molecule with a second functional group of a second protein molecule. In some embodiments, the first protein molecule is the same type as the second protein molecule. In some cases thereof, the first and second protein molecules are Type I collagen, while in others the first and second protein molecules are Type II collagen, and in still others the first and second protein molecules are a type of proteoglycan. In some embodiments, the first protein molecule is a different type than the second protein molecule. In some embodiments thereof, the first protein molecule is a type of collagen and the second protein molecule is a proteoglycan. In other embodiments thereof, the first protein molecule is Type I collagen and the second protein molecule is Type II collagen. In other embodiments thereof, the first protein molecule is a glycosaminoglycan and the second protein molecule is Type II collagen.

[0034] Direct crosslinking can be used in accordance with the present invention, and typically involves using the crosslinking agent as a bridge to chemically connect

one amino acid group on one protein molecule to another amino acid group on the same or different protein molecule. These agents are called bifunctional agents. In some preferred embodiments, the crosslinking agent comprises a pair of functional groups that react with amino acid groups on the native proteins to be linked. Preferably, these functional groups are aldehydes.

[0035] Direct crosslinking can be accomplished in either conventional one step or multistep procedures. Conventional methods of direct crosslinking are described by Khor (Biomaterials 18:95-105, 1997), which discloses methods for crosslinking collagenous tissues to improve durability, particularly transplant tissues from xenogeneic or allogeneic sources. In some embodiments of the present invention, direct crosslinking is accomplished in a one-step reaction, preferably by using a bifunctional agent. In some embodiments, the bifunctional agent is selected from the group consisting of dialdehydes, polyepoxy compounds and diisocyanates. One more preferred bifunctional agent used in accordance with the present invention is glutaraldehyde.

[0036] Conventional, multistep, direct, crosslinking reactions are also described by Khor. In some embodiments using multistep reactions, the bifunctional crosslinking agent is selected from the group consisting of acyl azide and carbodiimides.

[0037] Pathak et al. (Soc for Biomaterials 27th Annual Meeting Transactions p. 130, 2001) describe an alternative to glutaraldehyde fixation of bovine pericardium using bis-(sulphosuccinimidyl suberate) as the bifunctional agent. It is believed that bis(sulphosuccinimidyl suberate) may be less toxic than glutaraldehyde and is better resistant to calcification.

[0038] Crosslinking agents can also be made by attaching functional groups to synthetic polymers, which may improve biocompatibility. One particular example is functionally activating poly(ethylene glycol) with aldehyde groups to manufacture an agent that will directly crosslink tissues in a manner similar to glutaraldehyde and formaldehyde.

[0039] Preferably, the direct crosslinking agent of the present invention has a molecular weight of no more than 1 million Daltons. Above this preferred value, the crosslinking agent may be insoluble in water and may be very difficult to inject and disperse into the disc tissues. More preferably, the crosslinking agent has a molecular weight of between about 100 Daltons and about 100,000 Daltons. When the molecular weight of the agent is below about 100 Daltons, the agent may too easily diffuse into bodily tissues outside of the intervertebral disc. When the molecular weight of the agent is above about 100,000 Daltons, the agent may not disperse adequately within the disc tissues to cause uniform crosslinking of native molecules.

[0040] One preferred embodiment of this invention involves the direct, one step, aqueous reaction of a water-soluble, bifunctional crosslinking agent with at least a

portion of the native proteins of the intervertebral disc. Preferred crosslinking agents for this method include glutaraldehyde, bis(sulphosuccinimidyl suberate), polyepoxy compounds and bifunctionally activated synthetic polymers such as poly(ethylene glycol) dialdehyde. Preferably, the agent is diluted in a pH buffered physiological saline prior to administration. A buffered pH environment is desirable to maintain favourable reaction conditions during crosslinking.

[0041] Glutaraldehyde is particularly preferred as a crosslinking agent due to its medical history of use with biological transplant tissues and injectable adhesives. Preferably, the crosslinking agent (which is preferably glutaraldehyde) is delivered to the disc in a concentration of between approximately 0.1 and 20 volume percent (vol%), more preferably between 1 and 10 vol% in saline buffered to a pH of approximately 6.5 to 8.0, more preferably between approximately 7.0 to 7.5.

[0042] Another method of causing the crosslinking of native intervertebral disc molecular components is to chemically react target portions of native proteins (such as native collagen and/or native proteoglycan proteins) such that synthetic functional groups (such as aldehydes) are created directly on the native proteins. Crosslinking then preferably occurs between the synthetic functional groups (such as aldehyde groups) of the reacted native protein and an unreacted functional group (such as an amino acid group) located on either the same native protein or another molecule. Modification of the native component to form a functional group such as an aldehyde can be achieved using enzymatic oxidizing agents, and are preferably selected from the group consisting of lysine oxidase, transglutaminase, and multi-copper oxidases. Proteoglycans contain polysaccharide regions that may be modified to form aldehyde functional groups. This modification of proteoglycans may be accomplished by using either enzymatic or non-enzymatic agents. Examples of enzymatic polysaccharide oxidizing agents include catechol oxidase and tyrosinase. Examples of non-enzymatic polysaccharide oxidizing agents include periodate ions (periodic acid, sodium and potassium periodate), nitroprusside ions (sodium nitroprusside) and hydrogen peroxide.

[0043] In a preferred embodiment of this invention, a non-enzymatic polysaccharide oxidizing agent is injected into the nucleus pulposus of a pathological intervertebral disc. Because the dry weight component of the nucleus pulposus is rich in proteoglycans, there are numerous sites that can be oxidized to form functional aldehydes. Subsequently, the aldehydes can react with amino acid regions of both native collagens and native proteoglycans to form crosslinks.

[0044] Chemical modification of proteoglycans, particularly the sulphated proteoglycans, in the nucleus pulposus can elicit the added benefit of reducing the swelling pressure in the nucleus, thereby reducing both the potential for exuding out of the disc and the tendency

for the nucleus pulposus to cause bulging of the annulus. This is one proposed mechanism for the effectiveness of chemonucleolysis in reducing pain in properly selected patients (*Kato et al., Spine 17:934-939, 1992*). Furthermore, this mechanism is the basis for clinical experiments conducted with aprotinin, a protease inhibitor that forms strong complexes with sulphated glycosaminoglycans (*Kraemer et al., Spine 7:73-74, 1982*). **[0045]** Preferably, the indirect crosslinking agent of the present invention has a relatively low molecular weight, is substantially completely reacted in the crosslinking process, and forms by-products (such as gases and water) which can relatively easily exit the reaction site.

[0046] As is frequently the case with pathological intervertebral discs, concomitant with the presence of pain is a narrowing of the disc space and/or exuding of disc material (herniation) into the neural foramen. Likewise, the quantity of native tissue present in the disc may be lower than desired in order for crosslinking to restore the stability, biomechanics and disc height desired. Therefore, it may be desirable to add a supplemental protein into the disc as an adjunct to the crosslinking treatment. Preferably, the supplemental protein can be crosslinked by the same crosslinking agent used to crosslink the native proteins of the disc. Examples of supplemental proteins that are useful with the crosslinking strategies described above include but are not limited to collagen in various types and forms, hyaluronan, chondroitin sulphate, keratan sulphate, albumin, elastin, fibrin, fibronectin and casein.

[0047] Although the supplemental protein may be added before or after the crosslinking step, a preferred embodiment comprises the steps of first adding the supplemental material, then allowing or effecting the dispersion of the material into the disc space, then adding the crosslinking agent. Ultimately, this helps provide a more homogeneous crosslinked structure.

[0048] Therefore, in accordance with the present invention, there is provided a method of treating in a living being an intervertebral disc having native molecular proteins, comprising the steps of:

- (a) injecting a supplemental protein into the intervertebral disc, and
- (b) injecting a crosslinking agent into the intervertebral disc.

[0049] In preferred embodiments, the method comprises the sequential steps of:

- (a) injecting a supplemental protein into the intervertebral disc,
- (b) optionally dispersing the supplemental protein throughout at least the nucleus pulposus portion of the disc, and
- (c) injecting a crosslinking agent into the intervertebral disc.

[0050] Preferably, the crosslinking agent is injected in an amount sufficient to crosslink at least a portion of the native proteins. More preferably, the crosslinking agent is injected in an amount sufficient to crosslink at least a portion of the supplemental protein. In some embodiments, the supplemental protein is selected from the group consisting of collagen, hyaluronan, chondroitin sulphate, keratan sulphate, albumin, elastin, fibrin, fibronectin and casein. Preferably, when direct crosslinking is performed, the supplemental protein is collagen, and glutaraldehyde is preferably selected as the crosslinking agent. Preferably, when indirect crosslinking is performed, the supplemental protein is a polysaccharide (more preferably, hyaluronan) and sodium periodate is preferably selected as the crosslinking agent (which functions as a polysaccharide oxidizing agent). In some embodiments, the supplemental protein is injected substantially into the nucleus pulposus. More preferably, the crosslinking agent is also injected substantially into the nucleus pulposus. Because the supplemental protein can react with the crosslinking agent, in preferred embodiments, the crosslinking agent is provided in first sterile container and the supplemental protein is provided in a second sterile container.

[0051] Although the agents used in the disclosed invention are preferably non-toxic at the concentrations employed for treatment, it may be desirable to substantially inactivate any residual crosslinking agent with an inactivating agent once adequate crosslinking has been achieved in order to reduce any toxic potential the crosslinking agent may still possess. For example, a diluted solution of glycine will inactivate unreacted glutaraldehyde as disclosed in WO-01/70151). Because the inactivating agent can react with the crosslinking agent, in preferred embodiments, the crosslinking agent is provided in first sterile container and the inactivating agent is provided in a second sterile container.

[0052] In certain crosslinking procedures, the reaction is reversible, particularly if there is a dramatic change in pH. For these reversible reactions, it may be preferable to add a stabilizing agent once the crosslinking has been achieved. For example, the reaction of aldehyde functional groups with proteins generally forms what is known as a Schiff base, which may be a reversible reaction (with the exception of glutaraldehyde, which may undergo an irreversible reaction with proteins). In these cases where reverse reactions are possible, it may be preferable to include a later step of adding a stabilizing agent that substantially prevents the reversal of the crosslinking reaction. Preferred stabilizing agents comprise boron compounds. More preferred stabilizing agents are selected from the group consisting of sodium borohydride, sodium cyanoborohydride or pyridine borane. Pyridine borane is a more preferred agent for this invention due to its relatively higher biocompatibility. Because the stabilizing agent can react with the crosslinking agent, in preferred embodiments, the crosslinking agent is provided in a first sterile container and the stabilizing agent

is provided in a second sterile container.

[0053] In some embodiments, one or more of the compounds selected from the group consisting of the crosslinking agent, the supplemental protein, the inactivating agent and the stabilizing agent is delivered (preferably, separately) to the disc in a buffered saline solution capable of controlling pH during the crosslinking reaction. Preferably, the solution is buffered to a pH of approximately 6.5 to 8.0, more preferably between approximately 7.0 to 7.5.

[0054] In some embodiments, one or more of the compounds selected from the group consisting of the crosslinking agent, the supplemental protein, the inactivating agent and the stabilizing agent is delivered (preferably, separately) to the disc in a composition further comprising a radio-opaque contrast medium present in an amount sufficient to monitor the flow of the composition through fluoroscopy. In some embodiments, the radio-opaque contrast medium comprises iodine. In some embodiments, the radio-opaque contrast medium is an iodine-containing dye. In some embodiments, the radio-opaque contrast medium comprises a compound selected from the group consisting of barium-containing compounds (such as barium sulphate), zirconia and tantalum, is preferably a barium-containing compound, and more preferably is barium sulphate.

[0055] Therefore, in accordance with the present invention, there is provided a composition present within a natural intervertebral disc having a nucleus pulposus and an annulus fibrosus, comprising a crosslinked structure comprising:

- (a) proteins which are native to the intervertebral disc, and
- (b) a radio-opaque contrast medium present in an effective amount to be detected by fluoroscopy.

[0056] Also in accordance with the present invention, there is provided a composition for treating a natural intervertebral disc having native proteins, the composition comprising:

- (a) a crosslinking agent present in an effective amount for crosslinking both at least a portion of the native proteins, and
- (b) a radio-opaque contrast medium present in an effective amount to be detected by fluoroscopy.

[0057] In preferred embodiments, the compound is delivered in a buffered saline solution containing the radio-opaque contrast medium. In more preferred embodiments, each compound used in the procedure is delivered in a buffered saline solution containing the radio-opaque contrast medium.

[0058] When certain embodiments of the present invention are practised, there is produced a composition present within an intervertebral disc having a nucleus pulposus, comprising a crosslinked structure compris-

ing:

- (a) proteins which are native to the intervertebral disc, and
- (b) supplemental proteins.

[0059] In some embodiments, the crosslinked structure further comprises a direct crosslinking agent, preferably, glutaraldehyde.

[0060] In some embodiments, the native proteins are substantially derived from the nucleus pulposus.

[0061] When certain embodiments of the present invention are practised, there is produced a composition formed within an intervertebral disc having a level of naturally crosslinked proteins, the composition comprising a crosslinked structure comprising proteins which are native to the natural intervertebral disc, wherein the crosslinked structure has a degree of crosslinking which is higher than the unmodified level of naturally crosslinked proteins. Preferably, the naturally crosslinked proteins are unmodified.

[0062] In some embodiments, the crosslinked structure further comprises a direct cross linking agent, preferably glutaraldehyde. In others, the crosslinked structure has been crosslinked using an indirect crosslinking agent which is not incorporated into the crosslinked structure. Optionally, the crosslinked structure further comprises supplemental proteins. In preferred embodiments, the disc further comprises an annulus fibrosus having an inner wall, and wherein the crosslinked structure includes the inner wall of the annulus fibrosus. In others, the crosslinked structure is present essentially within the nucleus pulposus. In others, the crosslinked structure is present essentially throughout the entire disc.

[0063] In a preferred embodiment of the invention, the agents and materials to be delivered to the intervertebral disc are injected percutaneously under fluoroscopic control using a syringe and appropriate gauge needle, for example 25G. Such a minimally invasive procedure is highly desirable for minimizing damage to musculoskeletal structures and can be performed using an outpatient procedure. Although this injection can be delivered from any approach to the disc, it is preferable to use a posterior or posterolateral approach such that the needle is required to pass through a shortest distance before reaching the disc without penetrating major vascular or neural structures. Preferably, the agents and materials of this invention are injected into the centre of the nucleus pulposus of the disc such that the material can then disperse radially into the remainder of the nucleus pulposus and/or remainder of the disc.

[0064] The volume of diluted crosslinking solution injected into the disc is preferably between approximately 0.1 and 10 ml, more preferably between approximately 1 and 5 ml. This ensures that adequate crosslinking agent is delivered to the disc yet does not produce high pressures in the disc, potentially causing failure of the

disc and extruding of crosslinking agent and disc material. The volume of supplemental protein needed is preferably determined based on the amount of volume restoration needed to restore the disc to its natural size.

5 This can be determined using a combination of x-rays and MRI scans.

[0065] In another preferred embodiment, light exercising is used as an adjunct to the procedure in order to aid in the dispersing of agents and materials within the disc and to ensure complete reaction of the functional materials injected and/or generated. Examples of light exercise include limited left and right lateral bending, flexion and extension, and torso twists (axial rotation). Preferably, the light exercising is performed after each step of the treatment to disperse each agent or material prior to delivering a subsequent material.

[0066] As noted above, it is desirable to provide the different compounds used in the present invention in separate sterile containers in order to avoid undesirable reactions between them prior to their injection into the disc.

[0067] Therefore, in accordance with the present invention, there is provided a kit for injecting therapeutic solutions into an intervertebral disc having native proteins, comprising:

- (a) a first container having a sterile inner surface and containing a first compound, and
- (b) a second container having a sterile inner surface and containing a second different compound,

wherein the first and second compounds are selected from the group consisting of:

- (i) a crosslinking agent present in an effective amount for cross linking at least a portion of the native proteins,
- (ii) a supplemental protein,
- (iii) an inactivating agent, and
- (iv) a stabilizing agent.

[0068] In some embodiments, there is provided a third container having a sterile inner surface containing a third different compound selected from the above group of compounds. In other embodiments, there is provided a fourth container having a sterile inner surface containing a fourth different compound selected from the above group of compounds.

[0069] In preferred embodiments, at least one container containing a compound further contains a buffered saline solution, and preferably further contains a radio-opaque contrast medium. In more preferred embodiments, each provided container containing a compound further contains a buffered saline solution, and preferably further contains a radio-opaque contrast medium.

[0070] In preferred embodiments, the first container contains the crosslinking agent present in an effective

amount for crosslinking at least a portion of the native proteins, and the second container contains the supplemental protein.

[0071] In some preferred kit embodiments, the crosslinking agent is a direct crosslinking agent (such as glutaraldehyde) and the supplemental protein is collagen. In others, the crosslinking agent is an indirect cross linking agent (such as sodium periodate) and the supplemental protein is hyaluronan.

[0072] In some embodiments, the kit further comprises first and second sterile syringes for separately injecting the compounds. In other embodiments, third and preferably fourth syringes are also provided. In some embodiments, the containers of the kit are provided in a case. Likewise the syringes of the kit are provided in the case.

EXAMPLE 1 Biomechanical Testing of Cadaveric Functional Spine Units after Crosslinking Treatment

[0073] In a prophetic experiment, four human cadaveric lumbar spine segments (L1 - L5) are tested biomechanically to determine range-of-motion (ROM) in flexion-extension, lateral bending, axial torsion and pure compression to establish a baseline. Three crosslinking solutions plus one control solution are prepared: 1) 10% w/v glutaraldehyde in 0.1M phosphate buffered saline (PBS) with pH 7.4; 2) 10% w/v bis(sulphosuccinimidyl suberate) in PBS; 3) 10% sodium periodate in PBS; 4) PBS alone. For a given treatment, 2 ml of solution is injected into the centre of one of the four intervertebral discs of the cadaveric lumbar spine using a 5 ml syringe and 25G needle. For each spine segment, all treatments are applied, one to each level.

[0074] Following the injections, the spine segments are subjected to simulated light exercise, i.e. flexion-extension, lateral bending and axial rotation. These exercises are repeated at various times during the course of the experiment. After 2 hours and 24 hours, the biomechanical range-of-motion (ROM) testing is repeated to measure the effect of crosslinking on each motion segment.

[0075] The range of motion testing should indicate that the stiffness of the segments significantly increased over that of a normal untreated disc.

EXAMPLE 2 Outpatient Procedure for In Situ Crosslinking Treatment of the Intervertebral Disc

[0076] After complaining of low back and leg pain, a patient is referred to a spine specialist. Using x-rays and MRI, the physician determines that the pain is being caused by a bulging intervertebral disc with loss of disc height. The recommended treatment is restoration of disc height with an injection of soluble Type I atelocollagen followed by crosslinking treatment with 10% glutaraldehyde.

[0077] In the first outpatient procedure, 2 ml of atel-

opeptide Type I collagen solution is injected percutaneously into the centre of the intervertebral disc. The patient then follows a prescribed light exercise regimen of limited right and left lateral bending, flexion and extension, and torsional twisting and told to refrain from lifting heavy objects and engaging in high impact exercises.

[0078] The second outpatient procedure is performed on the following day. In this procedure, 2 ml of 10% glutaraldehyde solution in 0.1 M phosphate buffered saline (pH 7.4) is injected percutaneously into the centre of the intervertebral disc. Again, the patient then follows a prescribed light exercise regimen of limited right and left lateral bending, flexion and extension, and torsional twisting and told to refrain from lifting heavy objects and engaging in high impact exercises for at least two days.

Claims

1. A kit for injecting therapeutic solutions into an intervertebral disc having native proteins, comprising:
 - a. a first container having a sterile inner surface and containing a first compound, and
 - b. a second container having a sterile inner surface and containing a second different compound,
 wherein the first and second compounds are selected from the group consisting of:
 - i. a crosslinking agent present in an effective amount for crosslinking at least a portion of the native proteins,
 - ii. a supplemental protein,
 - iii. an inactivating agent, and
 - iv. a stabilizing agent.
2. The kit of claim 1 further comprising a third container having a sterile inner surface containing a third different compound selected from the group.
3. The kit of claim 2 further comprising a fourth container having a sterile inner surface containing a fourth different compound selected from the group.
4. The kit of claim 1 wherein at least one container containing a compound further contains a buffered saline solution and a radio-opaque contrast medium.
5. The kit of claim 1 wherein each container of the kit further contains a buffered saline solution, and preferably further contains a radio-opaque contrast medium.
6. The kit of claim 1 wherein the first container contains the crosslinking agent present in an effective

- amount for crosslinking at least a portion of the native proteins, and the second container contains the inactivating agent.
7. The kit of claim 1 wherein the first container contains the crosslinking agent present in an effective amount for crosslinking at least a portion of the native proteins, and the second container contains the supplemental protein. 5
 8. The kit of claim 7 wherein each container contains further contains a buffered saline solution and a radio-opaque contrast medium. 10
 9. The kit of claim 1 wherein the crosslinking agent is present in the first container in a concentration of between 0.1 and 20 volume percent. 15
 10. The kit of claim 1 wherein the cross linking agent is present in the first container in a concentration of between 1 and 10 volume percent. 20
 11. The kit of claim 1 further comprising first and second sterile syringes. 25
 12. The kit of claim 1 further comprising a case, wherein the containers are provided in the case. 30
 13. A composition present within an intervertebral disc having a nucleus pulposus and an annulus fibrosus, comprising a crosslinked structure comprising:
 - a. proteins which are native to the intervertebral disc, and
 - b. supplemental proteins. 35
 14. The composition of claim 13 wherein the crosslinked structure further comprises a direct crosslinking agent. 40
 15. The composition of claim 13 wherein the direct crosslinking agent is gluteraldehyde. 45
 16. The composition of claim 13 wherein the cross linked structure is present in the annulus fibrosus. 50
 17. The composition of claim 13 wherein the crosslinked structure is present substantially in the nucleus pulposus. 55
 18. A composition formed within a natural intervertebral disc having a level of naturally crosslinked proteins, the composition comprising a crosslinked structure comprising proteins which are native to the natural intervertebral disc, wherein the crosslinked structure has a degree of crosslinking which is higher than the level of naturally crosslinked proteins in the disc.
 19. The disc of claim 18 wherein the cross linked structure further comprises a direct cross linking agent.
 20. The disc of claim 18 wherein the naturally crosslinked proteins in the disc are unmodified.



European Patent
Office

PARTIAL EUROPEAN SEARCH REPORT

Application Number

which under Rule 45 of the European Patent Convention EP 03 25 1687 shall be considered, for the purposes of subsequent proceedings, as the European search report

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
D,X	WO 00 62832 A (ENDOSPINE LTD) 26 October 2000 (2000-10-26) * page 12, line 20 - line 21 * * page 15, line 13 - line 35 * * page 24, line 4 - line 5 * * page 25, line 35 - page 26, line 3 * * examples 1,2,7 * * claims 1,3,37; figure 1 * ---	1-12	A61L27/50
D,X	WO 01 70151 A (UNIV MICHIGAN) 27 September 2001 (2001-09-27) * page 1, line 13 - line 23 * * page 4, line 16 - line 26 * * page 6, line 31 - page 8, line 13 * * page 17, line 1 - line 14 * ---	1,5,6, 11,12	
P,X	WO 03 020031 A (HEDMAN THOMAS P ;UNIV SOUTHERN CALIFORNIA (US)) 13 March 2003 (2003-03-13) * page 3, line 4 - line 8 * * page 6, line 24 - page 7, line 11 * * page 8, line 3 - page 9, line 29 * * claims 1,4,5,7,9 * --- -/--	1-12	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			A61L
INCOMPLETE SEARCH			
<p>The Search Division considers that the present application, or one or more of its claims, does/do not comply with the EPC to such an extent that a meaningful search into the state of the art cannot be carried out, or can only be carried out partially, for these claims.</p> <p>Claims searched completely :</p> <p>1-12</p> <p>Claims searched incompletely :</p> <p>Claims not searched :</p> <p>13-20</p> <p>Reason for the limitation of the search:</p> <p>Article 53 (a) EPC - Contrary to "ordre public" or morality</p>			
Place of search		Date of completion of the search	Examiner
MUNICH		28 July 2003	Hars, J
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03.02 (P4/C07)



European Patent
Office

PARTIAL EUROPEAN SEARCH REPORT

Application Number
EP 03 25 1687

DOCUMENTS CONSIDERED TO BE RELEVANT			CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	
A	WO 01 76654 A (SULZER BIOLOG INC) 18 October 2001 (2001-10-18) * page 4, line 27 - page 5, line 19 * * page 21, line 3 - line 8 * * page 22, line 32 - page 23, line 1 * ---	1-12	
A	WO 97 26847 A (ADVANCED BIO SURFACES INC ; RYDELL MARK A (US); BAKER MATTHEW W (US) 31 July 1997 (1997-07-31) * page 4, line 18 - line 24 * * page 18, line 26 - page 19, line 30 * * claims 1,2,8-10 * ---	1-12	
A	WO 00 20021 A (KATIC VLADIMIR ; VUKICEVIC SLOBODAN (HR); SAMPATH KUBER T (US); STR) 13 April 2000 (2000-04-13) * example 9 * * claims 1,8,9,12,14,26,32 * ---	1-12	TECHNICAL FIELDS SEARCHED (Int.Cl.7)
A	US 4 931 546 A (TARDY MICHEL ET AL) 5 June 1990 (1990-06-05) * the whole document * -----	1-12	

EPO FORM 1503 02/02 (P04C10)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 03 25 1687

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

28-07-2003

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 0062832 A	26-10-2000	AU 4296200 A	02-11-2000
		WO 0062832 A1	26-10-2000
		EP 1173236 A1	23-01-2002
		US 2002198599 A1	26-12-2002
		US 6428576 B1	06-08-2002
WO 0170151 A	27-09-2001	US 6375672 B1	23-04-2002
		AU 3862801 A	03-10-2001
		WO 0170151 A1	27-09-2001
WO 03020031 A	13-03-2003	WO 03020031 A1	13-03-2003
		US 2003049301 A1	13-03-2003
WO 0176654 A	18-10-2001	CA 2400826 A1	18-10-2001
		EP 1272236 A1	08-01-2003
		WO 0176654 A1	18-10-2001
WO 9726847 A	31-07-1997	US 5888220 A	30-03-1999
		AU 1826497 A	20-08-1997
		CA 2244197 A1	31-07-1997
		EP 0886506 A1	30-12-1998
		JP 2001508317 T	26-06-2001
		WO 9726847 A1	31-07-1997
		US 2002156531 A1	24-10-2002
		US 2001004710 A1	21-06-2001
		US 6140452 A	31-10-2000
		US 6248131 B1	19-06-2001
		US 6306177 B1	23-10-2001
WO 0020021 A	13-04-2000	AU 5241799 A	26-04-2000
		AU 5330199 A	26-04-2000
		CA 2343698 A1	13-04-2000
		CA 2346375 A1	13-04-2000
		EP 1117422 A1	25-07-2001
		EP 1119611 A1	01-08-2001
		JP 2002526167 T	20-08-2002
		JP 2002526553 T	20-08-2002
		WO 0020021 A1	13-04-2000
		WO 0020559 A1	13-04-2000
		US 2002106362 A1	08-08-2002
		US 2001024823 A1	27-09-2001
US 4931546 A	05-06-1990	FR 2601371 A1	15-01-1988
		AT 114689 T	15-12-1994
		DE 3750793 D1	12-01-1995
		DE 3750793 T2	13-04-1995

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

